

TECHNICAL DATA SHEET ULTIMATE 2K HS CLEARCOAT AEROSOL

Date: 10-Jun-2024

DESCRIPTION

FL6000 **ULTIMATE 2K HS CLEARCOAT** aerosol is a ready for use product. (No hardener is required). Easy to use with good gloss levels. Perfect for SMART repairs and spot painting.

Composition: Shelf life: Pack size:	2K HS resins Correctly stored material, in a cool dry place will have a shelf life of 12 months. 400ml Aerosol Can
\triangle	Health and safety "For professional use only" Important: When using any new product, consult the "Health and Safety" data sheet. Always read the risks and precautions stated on the product label.
Ð	Clean the surface thoroughly using slow or fast degreaser.
	Shake can well before use 2-3 minutes.
15-20cm	Apply product spraying 15-20cm away from the panel being sprayed. DO NOT overload product onto the panel.
2-3 COATS	Spray 2 coats with 10 minutes flash-off in-between coats. Ensure previous coat is dry before applying the next coat. DO NOT apply more than the recommended number of coats. This will cause the products not to fully dry.
	Fully dried within 24 hours. Low hear may be used. This can be infrared (at a safe distance).

<u>Flash Point</u>

22°C – 30°C

The technical data contained herein is based on our present knowledge and we experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.